

## AMBERLITE FPA OH<sup>-</sup> ION EXCHANGE RESIN

02/24

### G-AMBOH

AMBERLITE™ FPA53 is an acrylic, weakly basic anion exchange resin containing tertiary amine functionality on a gel type acrylic matrix with no strongly basic functional sites. The acrylic polymer matrix is extremely flexible giving greater physical stability and organic fouling resistance to conventional polystyrene based resins. Less breakdown and less fouling leads to longer life in the application. Being a gel type resin AMBERLITE™ FPA53 has a higher capacity and is more durable than macroporous type resins.

#### PROPERTIES:

<b>Matrix:</b>	Crosslinked acrylic gel
<b>Functional group:</b>	Tertiary amines
<b>Physical form:</b>	Transparent white beads
<b>Ionic form:</b>	-OH
<b>Total exchange capacity:</b>	≥ 1.6 meq/mL (-OH)
<b>Moisture capacity:</b>	56 - 64%
<b>Shipping weight:</b>	700 g/L
<b>Harmonic mean size:</b>	0.50 to 0.75 mm
<b>Fines:</b>	< 0.30 mm 3.0% max
<b>Max reversible swelling:</b>	-OH → Cl <sup>-</sup> 30%

#### SUGGESTED OPERATING CONDITIONS:

<b>Max. temperature:</b>	50°C		
<b>Working flow rate:</b>	4 – 8 Bed Volumes per hour (BV/h)		
<b>Regenerant:</b>	NaOH	Na <sub>2</sub> CO <sub>3</sub>	NH <sub>4</sub>
<b>Concentration (%):</b>	2 – 4	5 - 8	1 - 4
<b>Regenerant level (g/L):</b>	130% of ionic load		
<b>Regeneration flow rate:</b>	2 - 8 (BV/h)	2 - 4 (BV/h)	2 - 4 (BV/h)
<b>Minimum contact time:</b>	30 min		
<b>Slow rinse:</b>	2 BV at regeneration flow rate		
<b>Fast rinse:</b>	8 - 16 BV at working flow rate		